



# Pebax® Co extrusion / Over Molding Compatibility

Insert Resin or Minor Component	2533	3533	4033	5533	6333	7033
2533	G	G	G	G	G	G
3533	G	G	G	G	G	G
4033	G	G	G	G	G	G
5533	F	F	G	G	G	G
6333	F	F	G	G	G	G
7033	F	F	G	G	G	G
Polyamide 11&12	F	F	G	G	G	G
Polyamide 6	P	P	P	P	P	P
Polycarbonate	G	G	G	G	G	G
Plasticized PVC	G	G	G	G	G	G
Rigid PVC	G	G	G	G	G	G
Polyurethane	G	G	G	F	F	F
EVA (28% VA)	G	G	G	G	G	G
EPR (Maleated)	G	G	G	G	G	G
Carboxyl NBR	G	G	G	G	G	G
Leather	G	G	G	G	G	G
<b>Compatibility :</b>	<b>G = Good</b>	<b>F = Fair</b>	<b>F = Fair</b>	<b>P = Poor</b>	<b>P = Poor</b>	<b>P = Poor</b>

Note : The general trends in alloy, insert mMolding and coextrusion compatibilities described above may vary depending on the specific processing parameters and additives used